

## PRODUCT INFORMATION



Baton Rouge Industries, Inc.  
5319 Groom Road • P.O. Box 26  
Baker, Louisiana 70714  
1-800-232-0334 • 225-775-3362  
FX 225-775-3498  
BatonRougeIndustries.com

# M-25 NON-MELT RED E.P. GREASE

“The Original Red Grease”

NLGI 1 & 2

08/01/17

### DESCRIPTION

M-25 Non-Melt Red E.P. Grease is a superior quality, multi-purpose E.P. grease formulated with PTFE to reduce friction and wear for heavy duty applications. M-25 Non-Melt Red E.P. Grease is formulated with organically treated bentone thickeners and will not melt and run out at high temperatures.

### COMPOSITION

M-25 Non-Melt Red E.P. Grease is formulated with virgin, 100% paraffin base oils with the highest natural film strength and viscosity index on the market today. In addition, M-25 Non-Melt Red E.P. Grease is fortified with the following additives, to enhance performance and provide optimum positive lubrication:

Rust & Oxidation Inhibitors	Anti-Wear Additives	Stabilizing Agents
Adhesive & Cohesive Additives	PTFE Resins	Oiliness Additives
Extreme-Pressure Additives	Friction Modifiers	

### APPLICATIONS

M-25 Non-Melt Red E.P. Grease is a versatile, multi-functional grease and is excellent in most applications where a high temperature or non-melt grease is applicable.

Chassis Lubrication	Anti-Friction Bearings	Roller Bearings	High Speed Bearings
Plain Bearings	Heavy Equipment	Sleeve Bearings	U-Joints
Slides & Ways	Flexible Couplings	Gear Motors	Fan Bearings
Conveyor Bearings	Slow Speed Bearings	Cables	

### PERFORMANCE CHARACTERISTICS

M-25 Non-Melt Red E.P. Grease is formulated for a wide range of applications to provide superior protection against:

Friction & Wear	Rust & Oxidation	Extreme Pressure	Shock Loads
Water Washout	Pound Out	High Temperatures	Abrasives

### SPECIFICATIONS

NLGI Grade	2	1
Base Oil @ 100 °F, SUS	450	100
Base Oil @ 210 °F, SUS	60	60
Worked Penetration	265-295	355-385
Thickner	Bentone	Bentone
Texture	Buttery/Stringy	Buttery
ASTM Dropping Point, °F	None	None
Timken Load Rating	65 lbs.	65 lbs.